

Material Declaration Form

Page 1

ams AG
Tobelbader Strasse 30
A-8141 Premstaetten, Austria
Tel +43 (0) 3136 500-0



Ordering Code	Package Family	Assembly Material Number	Lead Count	Weight (mg)	Manufacturing Country	Halogen Free	EU RoHS	China RoHS	Release Status	Version
AS5245-HMFP	MLF	177710115	32	135.18	Philippines	YES	YES	YES	FULL	1

Homogenous Material	Weight (mg)	Symbol	Chemical Substance	Input Ratio (%)	CAS Number	Unit Weight (mg)	Unit Weight (%)	Amount (ppm)
Leadframe	71.01	Ag	Silver	0.30	7440-22-4	0.21303	0.15759	1576
		Cu	Copper	97.25	7440-50-8	69.05723	51.08539	510854
		Fe	Iron	2.30	7439-89-6	1.63323	1.20819	12082
		Zn	Zinc	0.15	7440-66-6	0.10652	0.07879	788
Subtotal:				100.00		71.01000	52.52996	525300
Adhesive Bottom IC	0.98	Ag	Silver	84.00	7440-22-4	0.82068	0.60710	6071
			Epoxy Resin	16.00	25928-94-3	0.15632	0.11564	1156
Subtotal:				100.00		0.97700	0.72274	7227
IC Bottom	3.99	Si	Silicon	95.00	7440-21-3	3.78575	2.80053	28005
			Polyimide	5.00	58698-66-1	0.19925	0.14740	1474
Subtotal:				100.00		3.98500	2.94792	29479
Adhesive Spacer	0.28	SiO2	Silica Fused	34.00	60676-86-0	0.09588	0.07093	709
			Epoxy Resin	66.00	25928-94-3	0.18612	0.13768	1377
Subtotal:				100.00		0.28200	0.20861	2086
Spacer	2.34	Si	Silicon	100.00	7440-21-3	2.33900	1.73029	17303
Subtotal:				100.00		2.33900	1.73029	17303
Adhesive Top IC	0.28	SiO2	Silica Fused	34.00	60676-86-0	0.09588	0.07093	709
			Epoxy Resin	66.00	25928-94-3	0.18612	0.13768	1377
Subtotal:				100.00		0.28200	0.20861	2086

The information provided in this statement represents ams AG knowledge and belief as of the date that it is provided. ams AG bases its knowledge and belief on information provided by third parties, and makes no representation or warranty as to the accuracy and shall have no liability for the consequences of use of such information. ams AG has taken and continues to take reasonable steps to provide representative and accurate information but may not have conducted destructive testing or chemical analysis on incoming materials and chemicals. ams AG and its suppliers consider certain information to be proprietary, and thus CAS numbers and other limited information may not be available for release.

Material Declaration Form

Page 2

ams AG
Tobelbader Strasse 30
A-8141 Premstaetten, Austria
Tel +43 (0) 3136 500-0



Homogenous Material	Weight (mg)	Symbol	Chemical Substance	Input Ratio (%)	CAS Number	Unit Weight (mg)	Unit Weight (%)	Amount (ppm)
IC Top	3.99	Si	Silicon	95.00	7440-21-3	3.78575	2.80053	28005
			Polyimide	5.00	58698-66-1	0.19925	0.14740	1474
Subtotal:				100.00		3.98500	2.94792	29479
Wire	1.11	Au	Gold	99.00	7440-57-5	1.09890	0.81292	8129
			Pd	1.00	7440-05-3	0.01110	0.00821	82
Subtotal:				100.00		1.11000	0.82113	8211
Moldcompound	48.76	SiO2	Silica Fused	85.00	60676-86-0	41.44600	30.65986	306599
			Carbon Black	0.30	1333-86-4	0.14628	0.10821	1082
			Epoxy Resin	9.00	25928-94-3	4.38840	3.24634	32463
			Phenol Resin	5.70	28064-14-4	2.77932	2.05601	20560
Subtotal:				100.00		48.76000	36.07042	360704
Plating	2.45	Sn	Tin	100.00	7440-31-5	2.45000	1.81240	18124
Subtotal:				100.00		2.45000	1.81240	18124
Total:	135.18					135.18	100.00000	1000000

The information provided in this statement represents ams AG knowledge and belief as of the date that it is provided. ams AG bases its knowledge and belief on information provided by third parties, and makes no representation or warranty as to the accuracy and shall have no liability for the consequences of use of such information. ams AG has taken and continues to take reasonable steps to provide representative and accurate information but may not have conducted destructive testing or chemical analysis on incoming materials and chemicals. ams AG and its suppliers consider certain information to be proprietary, and thus CAS numbers and other limited information may not be available for release.