

Material Declaration Form

Page 1

ams AG
Tobelbader Strasse 30
A-8141 Premstaetten, Austria
Tel +43 (0) 3136 500-0



Ordering Code	Package Family	Assembly Material Number	Lead Count	Weight (mg)	Manufacturing Country	Halogen Free	EU RoHS	China RoHS	Release Status	Version
AS5311-ATST	TSSOP 4.4MM	179910017	20	81.51	Philippines	YES	YES	YES	FULL	1

Homogenous Material	Weight (mg)	Symbol	Chemical Substance	Input Ratio (%)	CAS Number	Unit Weight (mg)	Unit Weight (%)	Amount (ppm)
Leadframe	38.14	Ag	Silver	0.30	7440-22-4	0.11442	0.14038	1404
		Cu	Copper	95.90	7440-50-8	36.57626	44.87334	448733
		Mg	Magnesium	0.15	7439-95-4	0.05721	0.07019	702
		Ni	Nickel	3.00	7440-02-0	1.14420	1.40375	14038
		Si	Silicon	0.65	7440-21-3	0.24791	0.30415	3041
Subtotal:				100.00		38.14000	46.79180	467918
Adhesive	1.42	Ag	Silver	73.00	7440-22-4	1.03660	1.27175	12717
		BLO (1-10)	Gamma Butyrolactone	3.00	96-48-0	0.04260	0.05226	523
			Epoxy Resin	21.00	25928-94-3	0.29820	0.36584	3658
			Silver Oxide	3.00	1301-96-8	0.04260	0.05226	523
Subtotal:				100.00		1.42000	1.74212	17421
IC	6.65	Si	Silicon	100.00	7440-21-3	6.65000	8.15851	81585
Subtotal:				100.00		6.65000	8.15851	81585
Wire	0.42	Au	Gold	100.00	7440-57-5	0.42000	0.51527	5153
Subtotal:				100.00		0.42000	0.51527	5153
Moldcompound	32.93	SiO2	Silica Fused	85.00	60676-86-0	27.99050	34.33996	343400
			Carbon Black	0.30	1333-86-4	0.09879	0.12120	1212
			Epoxy Resin	9.00	25928-94-3	2.96370	3.63600	36360
			Phenol Resin	5.70	28064-14-4	1.87701	2.30280	23028
Subtotal:				100.00		32.93000	40.39995	404000

The information provided in this statement represents ams AG knowledge and belief as of the date that it is provided. ams AG bases its knowledge and belief on information provided by third parties, and makes no representation or warranty as to the accuracy and shall have no liability for the consequences of use of such information. ams AG has taken and continues to take reasonable steps to provide representative and accurate information but may not have conducted destructive testing or chemical analysis on incoming materials and chemicals. ams AG and its suppliers consider certain information to be proprietary, and thus CAS numbers and other limited information may not be available for release.

Material Declaration Form

Page 2

ams AG
Tobelbader Strasse 30
A-8141 Premstaetten, Austria
Tel +43 (0) 3136 500-0



Homogenous Material	Weight (mg)	Symbol	Chemical Substance	Input Ratio (%)	CAS Number	Unit Weight (mg)	Unit Weight (%)	Amount (ppm)
Plating	1.95	Sn	Tin	100.00	7440-31-5	1.95000	2.39234	23923
Subtotal:				100.00		1.95000	2.39234	23923
Total:	81.51					81.51	100.00000	1000000

The information provided in this statement represents ams AG knowledge and belief as of the date that it is provided. ams AG bases its knowledge and belief on information provided by third parties, and makes no representation or warranty as to the accuracy and shall have no liability for the consequences of use of such information. ams AG has taken and continues to take reasonable steps to provide representative and accurate information but may not have conducted destructive testing or chemical analysis on incoming materials and chemicals. ams AG and its suppliers consider certain information to be proprietary, and thus CAS numbers and other limited information may not be available for release.