

Material Declaration Form

Page 1

ams AG
Tobelbader Strasse 30
A-8141 Premstaetten, Austria
Tel +43 (0) 3136 500-0



Ordering Code	Package Family	Assembly Material Number	Lead Count	Weight (mg)	Manufacturing Country	Halogen Free	EU RoHS	China RoHS	Release Status	Version
AS5162-HSOM	SOIC 150 MIL	186210038	8	83.77	Philippines	YES	YES	YES	FULL	1

Homogenous Material	Weight (mg)	Symbol	Chemical Substance	Input Ratio (%)	CAS Number	Unit Weight (mg)	Unit Weight (%)	Amount (ppm)
IC	7.35	Si	Silicon	100.00	7440-21-3	7.35000	8.77402	87740
Subtotal:				100.00		7.35000	8.77402	87740
Moldcompound	38.1	SiO2	Silica Fused	86.00	60676-86-0	32.76600	39.11424	391142
			Carbon Black	0.50	1333-86-4	0.19050	0.22741	2274
			Epoxy Resin	7.50	25928-94-3	2.85750	3.41113	34111
			Phenol Resin	6.00	28064-14-4	2.28600	2.72890	27289
Subtotal:				100.00		38.10000	45.48168	454817
Wire	0.16	Au	Gold	99.00	7440-57-5	0.15840	0.18909	1891
		Pd	Palladium	1.00	7440-05-3	0.00160	0.00191	19
Subtotal:				100.00		0.16000	0.19100	1910
Plating	1.36	Sn	Tin	100.00	7440-31-5	1.36000	1.62349	16235
Subtotal:				100.00		1.36000	1.62349	16235
Adhesive	1.82	Ag	Silver	73.00	7440-22-4	1.32860	1.58601	15860
		BLO (1-10)	Gamma Butyrolactone	3.00	96-48-0	0.05460	0.06518	652
			Epoxy Resin	21.00	25928-94-3	0.38220	0.45625	4562
			Silver Oxide	3.00	1301-96-8	0.05460	0.06518	652
Subtotal:				100.00		1.82000	2.17262	21726

The information provided in this statement represents ams AG knowledge and belief as of the date that it is provided. ams AG bases its knowledge and belief on information provided by third parties, and makes no representation or warranty as to the accuracy and shall have no liability for the consequences of use of such information. ams AG has taken and continues to take reasonable steps to provide representative and accurate information but may not have conducted destructive testing or chemical analysis on incoming materials and chemicals. ams AG and its suppliers consider certain information to be proprietary, and thus CAS numbers and other limited information may not be available for release.

Material Declaration Form

Page 2

ams AG
 Tobelbader Strasse 30
 A-8141 Premstaetten, Austria
 Tel +43 (0) 3136 500-0



Homogenous Material	Weight (mg)	Symbol	Chemical Substance	Input Ratio (%)	CAS Number	Unit Weight (mg)	Unit Weight (%)	Amount (ppm)
Leadframe	34.98	Ag	Silver	0.30	7440-22-4	0.10494	0.12527	1253
		Cu	Copper	97.25	7440-50-8	34.01805	40.60887	406089
		Fe	Iron	2.30	7439-89-6	0.80454	0.96042	9604
		Zn	Zinc	0.15	7440-66-6	0.05247	0.06264	626
Subtotal:				100.00		34.98000	41.75719	417572
Total:	83.77					83.77	100.00000	1000000

The information provided in this statement represents ams AG knowledge and belief as of the date that it is provided. ams AG bases its knowledge and belief on information provided by third parties, and makes no representation or warranty as to the accuracy and shall have no liability for the consequences of use of such information. ams AG has taken and continues to take reasonable steps to provide representative and accurate information but may not have conducted destructive testing or chemical analysis on incoming materials and chemicals. ams AG and its suppliers consider certain information to be proprietary, and thus CAS numbers and other limited information may not be available for release.