

# Product Document

# Material Declaration Form

Page 1

ams AG  
Tobelbader Strasse 30  
A-8141 Premstaetten, Austria  
Tel +43 (0) 3136 500-0



Ordering Code	Package Family	Assembly Material Number	Lead Count	Weight (mg)	Manufacturing Country	Halogen Free	EU RoHS	China RoHS	Release Status	Version
TCS34007FNM	ODFN 2x2.4x0.65mm	503460002	6	7.11	Thailand	YES	YES	YES	FULL	1

Homogenous Material	Weight (mg)	Symbol	Chemical Substance	Input Ratio (%)	CAS Number	Unit Weight (mg)	Unit Weight (%)	Amount (ppm)
Leadframe	2.8	Ag	Silver	0.02	7440-22-4	0.00056	0.00788	79
		Au	Gold	0.03	7440-57-5	0.00084	0.01181	118
		Cu	Copper	96.20	7440-50-8	2.69360	37.88467	378847
		Fe	Iron	2.30	7439-89-6	0.06440	0.90577	9058
		Ni	Nickel	1.30	7440-02-0	0.03640	0.51195	5120
		Pd	Palladium	0.05	7440-05-3	0.00140	0.01969	197
		Zn	Zinc	0.10	7440-66-6	0.00280	0.03938	394
<b>Subtotal:</b>				<b>100.00</b>		<b>2.80000</b>	<b>39.38115</b>	<b>393812</b>
Adhesive	0.12	Al2O3	Aluminum Oxide	53.00	1344-28-1	0.06360	0.89451	8945
		SiO2	Silica Fused	8.00	60676-86-0	0.00960	0.13502	1350
			Epoxy Resin	31.00	25928-94-3	0.03720	0.52321	5232
			Hardener	8.00	620-92-8	0.00960	0.13502	1350
<b>Subtotal:</b>				<b>100.00</b>		<b>0.12000</b>	<b>1.68776</b>	<b>16878</b>
IC	0.75	Si	Silicon	100.00	7440-21-3	0.75000	10.54852	105485
<b>Subtotal:</b>				<b>100.00</b>		<b>0.75000</b>	<b>10.54852</b>	<b>105485</b>
Wire	0.04	Au	Gold	100.00	7440-57-5	0.04000	0.56259	5626
<b>Subtotal:</b>				<b>100.00</b>		<b>0.04000</b>	<b>0.56259</b>	<b>5626</b>
Moldcompound	3.4		Epoxy Resin	100.00	1675-54-3	3.40000	47.81997	478200
<b>Subtotal:</b>				<b>100.00</b>		<b>3.40000</b>	<b>47.81997</b>	<b>478200</b>
<b>Total:</b>	<b>7.11</b>					<b>7.11</b>	<b>100.00000</b>	<b>1000000</b>

The information provided in this statement represents ams AG knowledge and belief as of the date that it is provided. ams AG bases its knowledge and belief on information provided by third parties, and makes no representation or warranty as to the accuracy and shall have no liability for the consequences of use of such information. ams AG has taken and continues to take reasonable steps to provide representative and accurate information but may not have conducted destructive testing or chemical analysis on incoming materials and chemicals. ams AG and its suppliers consider certain information to be proprietary, and thus CAS numbers and other limited information may not be available for release.